

DESCOR®

Backlit

Fields of application

.01 .02 .04 .05 .07

Specifications



599239 193



100 % polyester
knit fabrics
PVC-free, recyclable



ca. 160/ 252 /320 cm
ca. 63/ 99/ 126 inch
other widths available on request



B-s1, d0 DIN EN 13501-1



ca. 250 g/m²
ca. 7.4 oz/yd²



ca. 0.52 mm
ca. 520 µm



rolls
50 m
55 yd



blank: 16.9 %
DIN EN 410



blank: 0.0 %
DIN EN 410



blank: 6
DIN EN ISO 105-B02



indirect, direct light



cold, ultrasonic cut



warp: 210.4 N
weft: 1840.8 N
DIN EN ISO 13934-1



warp: 55.0 %
weft: 42.4 %
DIN EN ISO 13934-1



warp: 1.5 %
weft: 1.3 %
DIN EN 14704-1

Printing methods

print	UV	Latex	Dyesub	UVgel
Inside			•	
Outside				

Article shrinkage

(50 sec hold up time)

	shrinkage in cross direction	shrinkage in longitudinal direction	recommended fixing temperature
180°C	0,4 %	1,9 %	
190°C	0,4 %	2,3 %	•
200°C	0,5 %	3,3 %	
210°C	0,6 %	3,8 %	

Certifications



DESCOR® Backlit

Fields of application

.01 .02 .04 .05 .07



Ref.-Nr.: 599239 193 | Preview print sample