

PrintTex® SUNTEX® I

Fields of application

.02 .05 .07 .08

Specifications

	REF. 564255 094
	100 % polyester weave fabrics, UV stable PVC-free, recyclable
	505 cm 199 inch other widths available on request
	ca. 245 g/m ² ca. 7.2 oz/yd ²
	ca. 0.4 mm ca. 400 µm
	rolls 50 m 55 yd
	blank: 7 DIN EN ISO 105-B02
	blank: 26.6 % DIN EN 410
	blank: 1.4 % DIN EN 410
	blank: 94.47 DIN 5033-1
	trapezoid tear resistance warp: 380.1 N weft: 184.7 N DIN EN ISO 9073-4
	maximum tensile strength warp: 1991.3 N weft: 2135.3 N DIN EN ISO 13934-1
	maximum tensile elongation warp: 56.0 % weft: 36.2 % DIN EN ISO 13934-1
	heat, ultrasonic cut

water repellency blank: 5 DIN EN ISO 4920
water absorption blank: 9.3 % DIN EN 29865 (Bundesmann)
lotus effect (after 10 min) blank: 1-2 DIN EN 29865 (Bundesmann)
water throughput blank: 8.6 ml DIN EN 29865 (Bundesmann)
oil repellent properties blank: 6 AATCC 118-1997
resistance to water blank: 25.2 mbar DIN EN 20811

Printing methods

print	UV	Latex	Dyesub	UVgel
Inside	•			
Outside	•			

Certifications



PrintTex® SUNTEX® I

Fields of application

.02 .05 .07 .08



Ref.-Nr.: 564255 094 | Preview print sample