

DirectTex® Blackout VI

Field of application

Blockout

Specifications



512335 009



100 % polyester
weave fabrics
PVC-free, recyclable



ca. 155/ 252/ 310/ 505 cm
ca. 61/ 99/ 122/ 199 inch
other widths available on request



B-s1, d0 DIN EN 13501-1



ca. 330 g/m²
ca. 9.7 oz/yd²



ca. 0.46 mm
ca. 460 µm



rolls
50 m
55 yd



warp: 380 N
weft: 468 N
DIN EN 1875-03



white (front): 5
black (back): 5-6
DIN EN ISO 105-B02



white (front): 12.62 %
DIN 5033



ultrasonic cut



200 Pa: 49.2 l/(m²s)
DIN EN ISO 9237



white (front): 0.2 %
black (back): 0.1 %
DIN EN 410



white (front): 0.0 %
black (back): 0.0 %
DIN EN 410

Printing methods

print	UV	Latex	Dyesub
Inside	•	•	•
Outside			

Article shrinkage

(50 sec hold up time)

	shrinkage in cross direction	shrinkage in longitudinal direction	recommended fixing temperature
180°C	0,8 %	1,1 %	•
190°C	1,2 %	1,7 %	
200°C	1,6 %	1,9 %	
210°C	2,4 %	2,6 %	

Certifications



DirectTex® Blackout VI

Field of application

Blockout



Ref.-Nr.: 512335 009 | Preview print sample